

Werkstoffnr.	EN/DIN Bezeichnung	Alternative Bez. 1	Alternative Bez. 2
1.0037	S235JR+C	ST 37-2	
1.0038	S235JR	ST 37-2	
1.0039	S235JRH		
1.0040		USt 42-2	
1.0042		RSt 42-2	
1.0044	S275JR	St 44-2	
1.0045	S355JR		
1.0114	S235J0		
1.0117	S235J2		
1.0345	P235GH		
1.0425	P265GH		
1.0473	P355GH		
1.0481	P295GH		
1.0482	P310GH		19Mn5
1.0545	S355N		
1.0570	S355J2	St 52-3	
1.0577	S355J2	St 52-3	
1.0579	S355J2		
1.0580	E355	St 52	
1.0581	St 52.4		
1.0585	St 52-3		
1.0592	E355J2		
1.0595	S355K2G3		
1.0596	S355K2G4		
1.0599	E420J2		
1.4027	GX20Cr14		
1.4034	X46Cr13		
1.4057	X17CrNi16-2		
1.4059	GX22CrNi17		
1.4301	X5CrNi18-10		V2A
1.4303	X4CrNi18-12		
1.4306	X2CrNi19-11		
1.4308	GX6CrNi18-9		
1.4310	X10CrNi18-8		
1.4311	X2CrNi18-9	X2CrNi18-10	
1.4319	X5CrNi17-7		
1.4362	X2CrNi23-4		
1.4371	X2CrMnNi17-7-5		
1.4401	X5CrNiMo17-12-2	X5CrNiMo18-10	AISI 316
1.4404	X2CrNiMo17-12-2	X2CrNiMo18-10	V4A
1.4406	X2CrNiMo17-11-2		AISI 316L
1.4408	GX5CrNiMo19-11-2	GX6CrNiMo18-10	
1.4409	GX2CrNiMo19-11-2		
1.4417	X2CrNiMoSi19-5	GX2CrNiMoN25-7-3	
1.4429	X2CrNiMo17-12-3		
1.4432	X2CrNiMo17-12-3		
1.4435	X2CrNiMo18-14-3	X2CrNiMo18-12	
1.4436	X5CrNiMo17-13-3	X5CrNiMo 18-12	
1.4437	GX6CrNiMo18-12		

1.4460	X3CrNiMoN27-5-2	X4CrNiMoN27-5-2	AISI 329
1.4462	X2CrNiMoN22-5-3		AISI 318LN
1.4463	GX6CrNiMo24-8-2		
1.4470	GX2CrNiMoN22-5-3		
1.4541	X6CrNiTi18-10		
1.4550	X6CrNiNb18-10	X10CrNiNb18-9	
1.4552	GX5CrNiNb18-9		
1.4571	X6CrNiMoTi17-12-2		
1.4573	X10CrNiMoTi18-12		
1.4580	X6CrNiMoNb17-12-2		
1.4581	X2CrNiMoN25-7-3		
1.4583	X10CrNiMoNb18-12		
1.4710	GX30CrSi7	GX30CrSi6	
1.4713	X10CrAlSi7	X10CrAl7	
1.4724	X10CrAlSi13	X10CrAl13	
1.4729	GX40CrSi13		
1.4740	GX40CrSi17		
1.4742	X10CrAlSi18	X10CrAl18	
1.4825	GX25CrNiSi18-9		
1.4828	X15CrNiSi20-12		AISI 309
1.4850	X15NiCrNb32-21		
1.4878	X8CrNiTi18-10	X12CrNiTi18-9	AISI 321H
1.4948	X6CrNi18-11	302mod	
1.5403	17MnMoV6-4		
1.5415	16Mo3	15Mo3	
1.5421	20MnMo3-5		
1.6311	20MnMoNi4-5		
1.6368	15NiCuMoNb5-6-4	15NiCuMoNb5	
1.6761	GS-18 NiMoCr 3 7	G18NiMoCr3-7	
1.6900	X12CrNi18-9		
1.6901	GX8CrNi18-10		
1.6902	GX6CrNi18-10		
1.6903	X10CrNiTi18-10		
1.6906	X5CrNi18-10		
1.7218	25CrMo4		AISI 4130H
1.7225	42CrMo4		AISI 4140
1.7258	24CrMo5		
1.7262	15CrMo5		
1.7276	10CrMo11		
1.7281	16CrMo9-3		
1.7335	13CrMo4-5	13CrMo4-4	
1.7354	G22CrMo5-4	GS22CrMo5-4	
1.7357	G17CrMo5-5	GS17CrMo5-5	
1.7375	12CrMo9-10		
1.7379	G17CrMo9-10	GS18CrMo9-10	
1.7380	10CrMo9-10		
1.7382	G19CrMo9-10		
1.7383	11CrMo9-10		
1.7728	16CrMoV4		
1.8901	S460N	StE 460	

1.8902	S420N	StE 420	
1.8903	S460NL	TStE 460	
1.8904	S550Q	StE 550 V	
1.8905	P460N		
1.8918	P460NL2	EStE 460	
1.8919	S500NL1	EStE 500	
1.8920	S690G1QL	TStE 690 VA	
1.8921	S690G2QL	TStE 690 VB	
1.8922	S690G4QL	TStE 690 VC	
1.8923	S590QL	TStE 590 V	
1.8924	S500Q	StE 500 V	
1.8925	S890QL1	EStE 890 V	
1.8926	S550QL	TStE 550 V	
1.8927	S620QL	TStE 620 V	
1.8928	S690QL	TStE 690 V	
1.8929	S690G3QL	TStE 690 VD	
1.8930	P380NH	WStE 380	
1.8931	S690Q	StE 690 V	
1.8932	P420NH	WStE 420	
1.8933	S960QL	TStE 960 V	
1.8934	S960QL1		
1.8983	S890QL	TStE 890 V	
3.1325	AlCuMg1	AlCuMgSi	EN AW 2017A
3.2315	AlSi1MgMn	AlMgSi1	EN AW 6082
3.3206	AlMgSi	AlMgSi0,5	EN AW 6060
3.3210	AlSiMg(A)	AlMgSi0,7	EN AW-6005A
3.3211	AlMg1SiCu		EN AW-6061
3.3241		G-/GK-/GF-AlMg3Si	
3.3261		G-/GK-AlMg5Si	EN AC-51400
3.3315	AlMg1		EN AW-5005
3.3525	AlMg2	AlMg2Mn0,3	EN AW-5241
3.3535	AlMg3		EN AW-5754
3.3537	AlMg3Mn	AlMg2,7Mn	EN AW-5454
3.3541		G-/GK-/GF-AlMg3(a)	EN AC-51100
3.3545	AlMg4	AlMg4Mn	EN AW-5086
3.3547	AlMg4,5Mn0,7	AlMg4,5Mn	EN AW-5083
3.3555	AlMg5		EN AW-5019
3.3561		EN AC-51300	G-/GK-AlMg5
3.4335	AlZn4,5Mg1	AlZn4,5Mg1	EN AW-7020
3.4365	AlZn5,5MgCu	AlZnMgCu1,5	EN AW-7075